## AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions, and listings, of claims in the application.

## Listing of Claims:

- (Cancelled)
- 2. (Previously Presented) The oriented syndiotactic polystyrene-based film of any one of claims 5 and 7, wherein (A) said water-dispersible polymer made by copolymerizing a monomer having an aromatic ring on its side chain with an acrylic monomer consists of a water-dispersible copolymer comprising a styrene monomer component and an acrylic monomer component as a major component, and the weight ratio of said styrene monomer component in said polymer is 0.15 to 0.85.
- (Currently Amended) The oriented syndiotactic polystyrene-based film of any one of claims [[2,]] 5 and 7 having a laminate strength of 50 gt/15 mm or higher.
- (Currently Amended) The oriented syndiotactic polystyrene-based film of any one of claims [[2,]] 5 and 7 having a waterproof laminate strength of 50 gf/15 mm or higher.
- 5. (Previously Presented) An oriented syndiotactic polystyrene-based film, comprising a film consisting of a styrene-based polymer having a syndiotactic structure, and a laminated adhesiveness-improving layer on at least one side of said film, wherein said layer comprises one or more of the following resins (A)-(H):
  - (A) a water-dispersible polymer made by copolymerizing a monomer having an aromatic ring on its side chain with an acrylic monomer;
  - (B) a water-dispersible copolymerized polyester having a glass transition temperature of 30°C or less, and/or a water-dispersible copolymerized polyester satisfying the following (1):
  - (1) a ratio of B / (A+B) is 0.07 to 0.25, wherein A and B are the integrated values at chemical shifts of 1.0 ppm to 6.0 ppm and 7.0 ppm to 9.0 ppm, respectively, in  $^{1}$ H NMR:

- (C) a water-soluble and/or a water-dispersible polyurethane resin;
- (D) a water-soluble and/or a water-dispersible polyamide resin;
- (E) a water-dispersible polyacrylonitrile resin;
- (F) a water-dispersible ethylene-vinyl ester copolymer resin;
- (G) a water-dispersible modified polyolefinic resin; and
- (H) a copolymer resin having an isobutylene unit, a maleic acid unit, and a nbutyl acrylate unit;

wherein said adhesiveness-improving layer comprises a polymer comprising a polystyrene sulfonate salt as a major component.

- 6. (Original) The oriented syndiotactic polystyrene-based film of claim 5, wherein said coated layer has a surface resistance value at 25°C and 60 RH % of 1 x  $10^{12}$   $\Omega/\Box$  or less.
- 7. (Currently Amended) An oriented syndiotactic polystyrene-based film, comprising a film consisting of a styrene-based polymer having a syndiotactic structure, and a laminated adhesiveness-improving layer on at least one side of said film, wherein said layer comprises one or more of the following resins (A)-(H):
  - (A) a water-dispersible polymer made by copolymerizing a monomer having an aromatic ring on its side chain with an acrylic monomer;
  - (B) a water-dispersible copolymerized polyester having a glass transition temperature of 30°C or less, and/or a water-dispersible copolymerized polyester satisfying the following (1):
  - (1) a ratio of B / (A+B) is 0.07 to 0.25, wherein A and B are the integrated values at chemical shifts of 1.0 ppm to 6.0 ppm and 7.0 ppm to 9.0 ppm, respectively, in  $^{1}$ H NMR:
    - (C) a water-soluble and/or a water-dispersible polyurethane resin;
    - a water-soluble and/or a water-dispersible polyamide resin;
    - (E) a water-dispersible polyacrylonitrile resin;
    - (F) a water-dispersible ethylene-vinyl ester copolymer resin;
    - (G) a water-dispersible modified polyolefinic resin; and
  - (H) a copolymer resin having an isobutylene unit, a maleic acid unit, and a nbutyl acrylate unit;

wherein a slipperiness-improving layer containing particles and/or-waxes is formed on a side of said adhesiveness-improving layer opposite to the side in contact with the at least one side of said film, wherein said slipperiness-improving layer consists of a composition comprising (a) a copolymerized polyester resin, (b) a compound having a sulfonate group, (c) particles having an average particle size of 1.0 to 5.0 µm, and (d) a polymeric wax.

## (Canceled)

- 9. (Previously Presented) The oriented syndiotactic polystyrene-based film of claim 5, wherein said adhesiveness-improving layer is formed on an unstretched film or a uniaxially oriented film consisting of a styrene-based polymer having a syndiotactic structure, and then stretching said film no near more in the uniaxial or biaxial direction, and thereafter subjecting said film to heat treatment.
- 10. (Currently Amended) The oriented syndiotactic polystyrene-based film of any one of claims [[2,]] 5 and 7, wherein said oriented syndiotactic polystyrene-based film comprises 3 to 30 parts by weight of at least one thermoplastic elastomer selected from a styrene-butadiene-styrene block copolymer (SBS), a styrene-isoprene-styrene block copolymer (SIS), and/or a hydrogenated compound thereof (SEBS and SEPS) on the basis of 100 parts by weight of the syndiotactic polystyrene-based polymer.
- 11. (Original) The oriented syndiotactic polystyrene-based film of claim 10, having a tensile impact strength of 0.65 j/mm² or higher, and a laminate strength of 50 gf/15 mm or higher.
- 12. (Previously Presented) The oriented syndiotactic polystyrene-based film of claim 7, wherein said adhesiveness-improving layer and/or slipperiness-improving layer is formed on an unstretched film or a uniaxially oriented film consisting of a styrene-based polymer having a syndiotactic structure, and then stretching said film once or more in the uniaxial or biaxial direction, and thereafter subjecting said film to heat treatment.